



	SPECIFICATIONS	
	JX265 PTFE MEMBRANE H13/H14	
Filtermaterial		100% Polyester
Construction		BICO Spun bond +THERMAL BONDED PTFE MEMBRANE
Treatment		
Permeability	m3/m2/h at 200 pa	100-110
Weight	g/m2	270
Elongation MD	%	35
Elongation CD	%	30
Thickness in mm	mm	0,54
Pore size	Micron	
Tenstile Strength MD	N	950
Tenstile Strength CD	N	850
Tear Strength MD	N	70
Tear Strength CD	N	40
Thermal Shrinkage MD	%	2,5
Thermal Shrinkage CD	%	0,5
Mullen Burst	Kg/cm2	35
Temperature Resistance	C	140
Hydrophobic Resistance		GOOD
Acid Resistance		GOOD
Alkaline Resistance		GOOD
Dust Release		EXCELLENT
Filter Test	EN1822-3:2009	H13 /H14
Efficiency of 0,1 Micron	%	H13: 99,988 H14: 99,995